

MIL-I-22444C Silicone Rubber Supported/Reinforced Self Fusing Limited Stretch Electrical Insulation Tape - Cable Splicing

Operating temperature: -65°F to +500°F / -54°C to 260°C; Brittle temperature -85°F / -65°C

FlameShield™ Meets MIL-I-22444 and ASNA 5107 Specifications

Self Binding Self-Fusing Tape - High Temperature, Heat & Flame Resistant



- Self-bonds / self fuses / self amalgamating. No sticky residue or adhesive when removed. Starts fusing within minutes, fully bonded within hours. Excellent cold weather and cryogenic performance.
- Excellent for sealing ends of firesleeve: protects sleeve from contamination and wicking liquids. Excellent for wrapping electrical & mechanical connections and splices. Makes clean and neat installations of cables, wires and hoses. Makes an instant separation bumper and provides vibration dampening. Secures insulation to hot air ducting.
- Meets Mil-i-22444C and other OEM specifications.
- Sinusoidal Fiberglass Reinforced with either 15% maximum stretch (SB15) or 25% maximum stretch (SA25) until failure of the reinforcement web.
- The embedded sinusoidal fiberglass layer provides limited stretch of the tape during installation, ensuring that a consistent minimum thickness is achieved during installation opposed to a variable thickness that occurs when manually adding tension to the tape during human applied scenarios. Machine applied tape tends to be much more uniform in thickness due to the automated tensioning measurement feedback in the application machinery.
- Supported/reinforced tape also prevents tape creep and fracturing when the tape is clamped with excessive force with either a connector back-shell, or installation clamp on a hydraulic fitting. The tape tends to remain in place and without layer fracturing compared to non supported/reinforced versions of the tape (MIL-I-46852 and A-A-59163 versions).
- Specified for cable splicing by the US Navy.
- Used as a compression protection tape under wiring connector back-shell clamping collars.
- CofC available.

The above picture of the clear version of the tape shows the fiberglass reinforcement layer. Tape is normally ordered in Oxide-Red or Black Color; other colors available including clear.

- Equivalent to MOX SA and MOX SB series tapes SB01020, SB00520, SB01015, SB01050 & SA00520, SA01020, SA03030, SA01015; DMS-2186 Type I, EMD/EMS 2074; General Dynamics P5189 & 5-00857; General Electric A50A493-C/D & A50E112; Grumman GT353V; RMS315 Type I; Simmonds 151274 (black); IBM 6084744; RL6000SA; RL6000SB; 68N, 69N, 78N, 79N; NSN 5970-01-325-8971; NSN 5970-00-841-1172; NSN 5970-14-464-7312; NSN 5970-01-596-7929

MIL-I-22444C Silicone Rubber Supported/Reinforced Self Fusing Limited Stretch Electrical Insulation Tape - Cable Splicing (Continued)

Operating temperature: -65°F to +500°F / -54°C to 260°C; Brittle temperature -85°F / -65°C
FlameShield™ Meets MIL-I-22444 and ASNA 5107 Specifications
Self Binding Self-Fusing Tape - High Temperature, Heat & Flame Resistant



- "S25" tape is 25% limited elongation
- "S15" tape is 15% limited elongation
- Meets 14 CFR 25.853(a) at amendment 25-116; Appendix F, Part I(a)(1)(i) (60 Second Vertical Flammability Test).

FlameShield™ MIL Spec High Temperature Silicone Self Fusing Compression/Stretch Tape Meets MIL-I-22444 Type I

Part Number	Tape Width Inches / mm	Thickness inches / mm	Type / Profile
MIL-I-22444-S25-M013-08-RXX-20	1/2 / 13	0.020 / 0.5	I / Rectangular
MIL-I-22444-S15-M013-08-RXX-20	1/2 / 13	0.020 / 0.5	I / Rectangular
MIL-I-22444-5970-00-446-8928-ROR*	1/2 / 13	0.020 / 0.5	I / Rectangular
MIL-I-22444-69N-RBK	3/4 / 19	0.020 / 0.5	I / Rectangular
MIL-I-22444-78N-ROR	1 / 25	0.020 / 0.5	I / Rectangular
MIL-I-22444-79N-RBK	1 / 25	0.020 / 0.5	I / Rectangular
MIL-I-22444-S25-M025-16-RXX-20	1 / 25	0.020 / 0.5	I / Rectangular
MIL-I-22444-S15-M025-16-RXX-20	1 / 25	0.020 / 0.5	I / Rectangular
MIL-I-22444-S25-M025-16-RXX-40	1 / 25	0.040 / 1.0	I / Rectangular

*5970-00-446-8928 was originally specified at 0.018" thick but is no longer produced in that thickness. Replacement is MIL-I-22444-5970-00-446-8928-OR and is 0.020" thick.

Please enquire for pricing on sizes other than those listed above.

- Standard roll length is 36 feet / 12 Yards / 10.9 Metres. * roll length 60 feet / 20 yards
- For the XX value (color code): OR = Oxide-Red, BK = Black. Clear & other colors available.
- Certificate of Conformity: Add \$6.00 for individual roll CofC. Lot/Batch CofC \$25.00 per order line item.
- Test Report: Add \$150.00 per order line item.

Amalgamating time: At 120°C; 120 minutes / at 150°C; 35 minutes / at 200°C; 20 minutes / at 250°C; 15 minutes

Tested for short duration fluid resistance: Jet Fuel (JP5), Hydraulic Fluid (Skydrol 500B4), Mineral Oil (NATO 0142), Synthetic Oil (NATO 0156), MIL-C-87836 & Foran 141B cleaning fluids, MIL-A-8243 cooling fluid.

These tapes are guaranteed to meet specification for 1 year from date of manufacture providing tapes are stored dry at 21°C +/- 3°C or 70°F +/- 5°F. Standard tapes have an interleaved liner of polyethylene. Polyester liner available.